

No.: GZMR120924407

Date: Oct. 31, 2012

Page: 2 of 6

Test Summary:

The following tests have been requested, also according to EN 14041-2004COR.2:2006, CE harmonized standard: Resilient, textile and laminate floor coverings — Essential Characteristics:

No.	Test item	Test method	Test result	Conclusion
Ĭ	Reaction to fire	EN 14041-2004COR.2: 2006 Clause 4.1	Class F _{fl}	5553
2	Content of pentachlorophenol (PCP)	EN 14041-2004COR.2: 2006 Clause 4.2	N.D.	Pass
3	Formaldehyde emission	EN 14041-2004COR.2: 2006 Clause 4.3	N.D. Class E 1	
4	Slip resistance	EN 14041-2004COR.2: 2006 Clause 4.5	Dynamic coefficient of friction: 0.34 Technical class DS	Pass
5	Thermal Conductivity	EN 14041-2004COR.2: 2006 Clause 4.7	0.198 W/(m·K)	(345)

Note: 1. Class F_{fl} is claimed without further testing.

- 2. N.D.= Not Detected (< MDL)
- 3. The above result was the average value.

******* To be continued******

ument is issued by the Companyunder its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/ferms.and.conditions.intion is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained here on the contained here only the contained here only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced for the contained here only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced for any prior above the company.



No.: GZMR120924407

Date: Oct. 31, 2012

Page: 3 of 6

Test Information:

Sample description: Board (see photo)

1. Reaction to fire

Test Method:

EN 14041-2004COR.2:2006 Clause 4.1

When declared, the floor covering shall be tested and classified according to the requirements of EN 13501-1:2007+A1:2009 and resulting class and subclass shall be declared.

If it is decided to make no claim of reaction for fire performance, which marked class F_{fl}, no testing is required

Test Result:

Reaction to fire class: F_{fl}

This reaction to fire class F_{ff} is claimed without further testing.

2. Content of pentachlorophenol (PCP)

Test Method:

EN 14041-2004COR.2:2006 Clause 4.2

Test Result:

Test Item	Unit	Result	MDL
Content of Pentachlorophenol	mg/kg	N.D.	1.0

Note:

- 1. 1 mg/kg = 1 ppm = 0.0001%
- 2. N.D. = Not Detected (< MDL)
- 3. MDL = Method Detection Limit

******* To be continued******

nent is issued by the Companyunder is General Conditions of Service printed overleaf or available on request and accessible at http://www.sqs.com/terms.and.conditions.ion.is. frawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained here on a few properties of the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this above not acceptable to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or not fite contents appearance of this document is unlawful and offenders may be prosecuted to the full estextent of the law.

erwise stated they exists shown in this test reportrefer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced in the law of the Company.



No.: GZMR120924407

Date: Oct. 31, 2012

Page: 4 of 6

Standard's Requirement:

Resilient, textile and laminate floor coverings shall not contain PCP or a derivative thereof as a component in the production process of the product or of its raw materials. In cases where verification is required, if the content is less than 5ppm in the parts of the product affected by treatment, this requirement shall be considered to be met.

Conclusion: Pass

3. Formaldehyde emission (In air)

Test Method:

EN 14041-2004COR.2:2006 Clause 4.3 and EN 717-1:2004

When formaldehyde-containing materials have been added to the product as a part of the production process. The product shall be tested and classified into one of two classes; E1 or E2.

Formaldehyde class E1: ≤0.124 mg/m³ air

Formaldehyde class E2: > 0.124 mg/m³ air

Test Result:

Test Item(s)	Unit	Result	MDL	Classification
Formaldehyde emission (In air)	mg/m³	N.D.	0.080	Class E1

Note:

- 1. N.D. = Not Detected (< MDL)
- 2. MDL = Method Detection Limit
- 3. mg/m3 = Milligrame per cubic meter

******* To be continued******

ument is issued by the Companyunder is General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms.andconditions.
ntion is drawn to the limitation of lability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained here on
because in findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this
labeled to report apparties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or
on of the contents appearance of this document is unlawful and offenders may be prosecuted to the fullestextent of the law.
therwise stated this results shown in this test reportrefer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced
full warm as prior approval of the Company.



No.: GZMR120924407

Date: Oct. 31, 2012

Page: 5 of 6

4. Slip resistance

Test Method:

EN 14041-2004COR.2:2006 Clause 4.5 and EN 13893:2002

The test was conducted in accordance with EN 13893:2002. Sliders made from the defined material and having a definite shape are loaded to impose a specified force on the floor covering. The loaded sliders are pulled parallel to the surface of floor covering at constant speed 0.2m/s to 0.3m/s. The horizontal force applied to pull the sliders is recorded over the length of a trace at least 0.30m. And the results were calculated by the formulae below:

 $\mu = F/M$

F- is the average horizontal force (in Newton).

M- is the total vertical load on the sliders (in Newton).

Test Condition:

Test speed: 0.26m/s

Test Result:

Specimen No.	1	2	3	4	5
Specimen thickness (mm)	10.55	10.55	10.55	10.55	10.55
Dynamic coefficient of friction	0.34	0.34	0.34	0.34	0.34
Average dynamic coefficient of friction	0.34				
Classification of dynamic coefficient of friction	1.	Technical class DS			

Standard's Requirement:

When declared, the floor covering intended to be used in dry and non-contaminated conditions shall have a dynamic coefficient of friction of ≥0.30 when tested ex-factory under dry conditions per EN 13893:2002 and shall be declared as technical class DS.

Conclusion: Pass

********To be continued******

ument is issued by the Companyunder its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms.andconditions. antion is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained here on the support of the properties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or ion of the contents appearance of this document is unlawful and offenders may be prosecuted to the full estextent of the law. there was a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or ion of the contents of the law. there was a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or ion of the contents of the law.



No.: GZMR120924407

Date: Oct. 31, 2012

Page: 6 of 6

5. Thermal Conductivity

Test Method:

EN 14041-2004COR.2:2006 Clause 4.7 and EN 12667:2001

Test Condition:

Lab environmental condition: 23±2℃, 50±5%RH

Sample size: 300×285×11.2mm, jointed with four pieces

Mean temperature: 25.27°C


Temperature difference: 9.34°C

Test Result: 0.198 W/(m·K)

Note: 1. The test result can not be compared with other results obtained from different test conditions, and should not be cited to the use condition directly.

2 The test item 5 was carried out by a SGS laboratory.

Photo:



*******End of report******

is issued by the Companyunder its General Conditions of Service printed overleafor available on request and accessible at http://www.ags.com/ferms.and.conditions.udrawnto the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained here on proceed in the time of its intervention only and within the limits of Client's instructions, if any. The Company's acid responsibility is to its Client and this not exponsibility as a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or here or appearance of this document is unlawful and offenders may be prosecuted to the full estextent of the law. sults shown in this test reportrefer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced proval of the Company.